

SPECIFICATION

Cycloaliphatic Epoxy Resins

Parameters	Specification
Appearance	Colorless to pale yellow
Molecular Weight	390.41 g/mol
Boiling Point	305 °C
Melting Point	-40 °C
Flash Point	170 °C
Purity	98–99%
Refractive Index	1.52
Solubility	Soluble in most organic solvents, insoluble in water
Uses	Coatings, adhesives, composites, encapsulation