

SPECIFICATION

Cellulose Acetate Butyrate

Parameters	Specification
CAS Number	9004-36-8
Appearance	White to pale amber solid resin
Molecular Weight	90000 g/mol
Boiling Point	360 °C
Flash Point	170 °C
Purity	98–99%
Refractive Index	1.5
Solubility	Soluble in acetone, ethyl acetate, and methyl ethyl ketone; insoluble in water
Uses	Coatings, paints, laminates, adhesives; film-forming resin for architectural and industrial coatings

+91-9227788155 | +91-9227788115 | +91-9227070667 | +91-260-6618618

info@triveniinterchem.com | info@trivenichemical.com

www.triveniinterchem.com | www.trivenichemical.com

135, Pancharatna, Char Rasta, G.I.D.C., Vapi-396195, Gujarat, India



www.chemicalbull.com

GROUP OF Triveni CHEMICALS