

SPECIFICATION

Polyvinyl Butyral

Parameters	Specification
CAS Number	63148-65-2
Appearance	White to off-white granular solid
Molecular Formula	(C ₈ H ₁₄ O ₂) _n
Molecular Weight	120000 g/mol
Boiling Point	400 °C
Flash Point	230 °C
Purity	98–99%
Refractive Index	1.49
Solubility	Soluble in acetone, MEK, and tetrahydrofuran; insoluble in water
Uses	Interlayer for laminated safety glass; adhesives; coatings

+91-9227788155 | +91-9227788115 | +91-9227070667 | +91-260-6618618

info@triveniinterchem.com | info@trivenichemical.com

www.triveniinterchem.com | www.trivenichemical.com

135, Pancharatna, Char Rasta, G.I.D.C., Vapi-396195, Gujarat, India



www.chemicalbull.com

GROUP OF Triveni CHEMICALS