

SPECIFICATION

Epoxidised Soyabean Oil

Parameters	Specification
Appearance	Yellow to amber viscous liquid
Molecular Weight	1000 g/mol
Boiling Point	330 °C
Melting Point	-20 °C
Flash Point	230 °C
Purity	98–99%
Refractive Index	1.47
Solubility	Insoluble in water; soluble in organic solvents
Uses	Plasticizer for PVC and other polymers; stabilizer in polymer formulations