

SPECIFICATION

Fumed Silica Hydrophilic

Parameters	Specification
Appearance	White powder
Molecular Weight	60.08 g/mol
Boiling Point	2230 °C
Melting Point	1700 °C
Flash Point	Not applicable
Purity	99.8–99.9%
Refractive Index	1.46
Solubility	Insoluble in water
Uses	Filler; rheology modifier for polymers and coatings; reinforcing filler for rubber

☎ +91-9227788155 | +91-9227788115 | +91-9227070667 | +91-260-6618618

✉ info@triveniinterchem.com | info@trivenichemical.com

🌐 www.triveniinterchem.com | www.trivenichemical.com

📍 135, Pancharatna, Char Rasta, G.I.D.C., Vapi-396195, Gujarat, India



www.chemicalbull.com

GROUP OF Triveni CHEMICALS