

## SPECIFICATION

### Zirconium Octate 12%

| Parameters       | Specification                                                            |
|------------------|--------------------------------------------------------------------------|
| Appearance       | Yellow-brown liquid                                                      |
| Molecular Weight | 664.06 g/mol                                                             |
| Boiling Point    | 320 °C                                                                   |
| Melting Point    | 10 °C                                                                    |
| Flash Point      | 140 °C                                                                   |
| Purity           | 12–12%                                                                   |
| Refractive Index | 1.46                                                                     |
| Solubility       | Water-insoluble, soluble in organic solvents such as toluene and xylene  |
| Uses             | Catalyst and drying agent, used in coatings and polymerization processes |